

Table 4.

Distribution of thicknesses of window glass in wood and clay lined cellar holes.

	East Barracks			West Barracks				
	Wood	Clay	Clay	Wood	Wood	Wood	Clay	Clay ¹
.8-.9 mm.		5	1			1		
1-1.1 mm.	25	36	4	3	8	6	3	1
1.2-1.3 mm.	23	36	8	10	16	12	5	5
1.4-1.5 mm.	29	41	18	11	21	5	5	3
1.6-1.7 mm.	15	24	8	12	26	16	13	4
1.8-1.9 mm.	13	14	6	14	19	9	20	6
2-2.1 mm.	9	10	6	23	9	5	12	2
2.2-2.3 mm.	3	6		3	3			
2.4-2.5 mm.		2			1		2	
2.6-2.7 mm.		2			2			2
2.8-2.9 mm.	1			1	1			4
3-3.1 mm.	1	1						5
3.2-3.3 mm.								3
Total	119	177	51	77	106	54	60	35
Mean	1.48	1.47	1.52	1.74	1.63	1.53	1.74	1.88
Standard Deviation	.3810	.3919	.2993	.3486	.3600	.3400	.3066	.7375

¹ Distributed by utility lines.